

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499

## Group Number Assessment

(In accordance with AS 5637.1-2015)

This is to confirm that the product as described below has been tested by AWTA Product Testing .

Testing was performed in accordance with AS/NZS 3837-1998 Method of test for heat and smoke release rates for materials and products using an oxygen consumption calorimeter.

**Test Sponsor :** Egger Australasia Pty Ltd  
PO Box 697  
Carlton South VIC 3053

**Test Number :** 19-001907  
**Issue Date :** 11/07/2019  
**Print Date :** 11/07/2019

**Sponsor Product** Clients Ref : "Flammex Eurodekor"  
Laminated Rigid Panel  
Colour : Timber look  
End Use : Joinery, Wall Panelling, Doors, Floors  
Nominal Composition : Wood Chip encased in a curable resin core with a melamine impregnated decor paper  
Nominal Mass per Unit Area/Density : 900kg/m3  
Nominal Thickness : 18mm

Product Group Number Classification : 1  
Average Specific Extinction Area : 20.0 m<sup>2</sup>/kg



Fiona McDonald  
Testing Technologist

35321

The message/document(s) contained in this electronic attachment is intended for the party to which it is addressed and may contain confidential information or be subject to professional privilege. It's transmission is not intended to place the contents into the public domain.

If you have received this transmission in error, it's disclosure or copying is prohibited . Please contact us by collect call so that arrangements can be made at our expense to rectify the error.

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing  
A.B.N 43 006 014 106  
1st Floor, 191 Racecourse Road, Flemington, Victoria 3031  
P.O Box 240, North Melbourne, Victoria 3051  
Phone (03) 9371 2400 Fax (03) 9371 2499

## TEST REPORT

**Client :** Egger Australasia Pty Ltd  
PO Box 697  
Carlton South VIC 3053

**Test Number :** 19-001907  
**Issue Date :** 10/07/2019  
**Print Date :** 11/07/2019

**Sample Description** Clients Ref : "Flammex Eurodekor"  
Laminated Rigid Panel  
Colour : Timber look  
End Use : Joinery, Wall Panelling, Doors, Floors  
Nominal Composition : Wood Chip encased in a curable resin core with a melamine impregnated decor paper  
Nominal Mass per Unit Area/Density : 900kg/m<sup>3</sup>  
Nominal Thickness: 18mm

### AS/NZS 3837-1998

Method of Test for Heat and Smoke Release Rates for Materials and Products using an Oxygen Consumption Calorimeter

Date Tested 10/07/2019  
Operator AWTA Test Operator 1  
Face Tested Melamine Face

	Specimen				
	1	2	3	Mean	
Average Heat Release Rate	30.4	30.4	34.9	31.9	kW/m <sup>2</sup>
Average Specific extinction area	17.8	25.8	16.5	20.0	m <sup>2</sup> /kg

(according to Specification C1.10 of the Building Code of Australia)

Test orientation : Horizontal

	Specimen				
	1	2	3	Mean	
Irradiance	50	50	50	50	kW/m <sup>2</sup>
Exhaust flow rate	0.024	0.024	0.024	0.024	m <sup>3</sup> /s
Time to sustained flaming	100	107	79	95	sec
Test duration	528	438	407	458	sec
Peak heat release after ignition	60.6	53.2	63.8	59.2	kW/m <sup>2</sup>
Average heat at 60 s	52.8	48.1	61.6	54.2	kW/m <sup>2</sup>

103279

35321

Page 1 of 8

© Australian Wool testing Authority Ltd  
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing  
- Chemical Testing  
- Mechanical Testing  
- Performance & Approvals Testing

: Accreditation No. 983  
: Accreditation No. 985  
: Accreditation No. 1356



Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)  
MANAGING DIRECTOR

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing  
A.B.N 43 006 014 106  
1st Floor, 191 Racecourse Road, Flemington, Victoria 3031  
P.O Box 240, North Melbourne, Victoria 3051  
Phone (03) 9371 2400 Fax (03) 9371 2499

## TEST REPORT

**Client :** Egger Australasia Pty Ltd  
PO Box 697  
Carlton South VIC 3053

**Test Number :** 19-001907  
**Issue Date :** 10/07/2019  
**Print Date :** 11/07/2019

Average heat at 180 s	47.8	43.3	48.2	46.4	kW/m <sup>2</sup>
Average heat at 300 s	36.9	32.0	36.5	35.1	kW/m <sup>2</sup>
Total heat released	13.0	10.1	11.6	11.6	MJ/m <sup>2</sup>
Average effective heat of combustion	4.2	4.0	4.8	4.3	MJ/kg
Initial thickness	18	18	18	18.0	mm
Initial mass	178.1	177.0	176.9	177.3	g
Mass at sustained flaming	175.1	173.6	174.5	174.4	g
Mass remaining	152.7	156.7	157.5	155.6	g
Mass percentage pyrolysed	14.3	11.5	10.9	12.2	%
Mass loss	3.1	2.5	2.4	2.7	kg/m <sup>2</sup>
Average rate of mass loss	7.3	7.6	7.3	7.4	g/m <sup>2</sup> .s
Additional Observations	None				
Difficulties Encountered during Testing	None				

These test results relate only to the behaviour of the product under the conditions of the test, they are not intended to be the sole criterion for assessment of performance under real fire conditions.

The results of these fire tests may be used to directly assess fire hazard, but it should be recognised that a single test method will not provide a full assessment of the fire hazard under all fire conditions.

Tests were conducted with a wire grid placed over the sample during testing. This was done to contain intumescent sample within the sample holder.

103279

35321

Page 2 of 8

© Australian Wool testing Authority Ltd  
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing  
- Chemical Testing  
- Mechanical Testing  
- Performance & Approvals Testing

: Accreditation No. 983  
: Accreditation No. 985  
: Accreditation No. 1356



Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)  
MANAGING DIRECTOR

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499


## TEST REPORT

**Client :** Egger Australasia Pty Ltd  
PO Box 697  
Carlton South VIC 3053


**Test Number :** 19-001907  
**Issue Date :** 10/07/2019  
**Print Date :** 11/07/2019

**Specimen :** 1


**Heat release rate (kW/m<sup>2</sup>)**




**Effective heat of combustion (MJ/kg)**



**Smoke production rate ([m<sup>2</sup>/s])**



**Specific extinction area (m<sup>2</sup>/kg)**



103279

35321

Page 3 of 8

© Australian Wool testing Authority Ltd  
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

- Chemical Testing  
- Mechanical Testing  
- Performance & Approvals Testing

: Accreditation No. 983  
: Accreditation No. 985  
: Accreditation No. 1356



Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)  
MANAGING DIRECTOR

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051


Phone (03) 9371 2400 Fax (03) 9371 2499

## TEST REPORT


**Client :** Egger Australasia Pty Ltd  
PO Box 697  
Carlton South VIC 3053

**Test Number :** 19-001907  
**Issue Date :** 10/07/2019  
**Print Date :** 11/07/2019


Mass loss rate (g/s)




Total heat released (MJ/m²)



Mass (g)



Rate of smoke release ([m²/s]/m²)



103279

35321

Page 4 of 8

© Australian Wool testing Authority Ltd  
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

- Chemical Testing  
- Mechanical Testing  
- Performance & Approvals Testing

: Accreditation No. 983  
: Accreditation No. 985  
: Accreditation No. 1356



Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)  
MANAGING DIRECTOR

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499


## TEST REPORT

**Client :** Egger Australasia Pty Ltd  
PO Box 697  
Carlton South VIC 3053


**Test Number :** 19-001907  
**Issue Date :** 10/07/2019  
**Print Date :** 11/07/2019

**Specimen :** 2


**Heat release rate (kW/m<sup>2</sup>)**




**Effective heat of combustion (MJ/kg)**



**Smoke production rate ([m<sup>2</sup>/s])**



**Specific extinction area (m<sup>2</sup>/kg)**



103279

35321

Page 5 of 8

© Australian Wool testing Authority Ltd  
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

- Chemical Testing  
- Mechanical Testing  
- Performance & Approvals Testing

: Accreditation No. 983  
: Accreditation No. 985  
: Accreditation No. 1356



Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)  
MANAGING DIRECTOR

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051


Phone (03) 9371 2400 Fax (03) 9371 2499

## TEST REPORT


**Client :** Egger Australasia Pty Ltd  
PO Box 697  
Carlton South VIC 3053

**Test Number :** 19-001907  
**Issue Date :** 10/07/2019  
**Print Date :** 11/07/2019


Mass loss rate (g/s)




Total heat released (MJ/m²)



Mass (g)



Rate of smoke release ([m²/s]/m²)



103279

35321

Page 6 of 8

© Australian Wool testing Authority Ltd  
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

- Chemical Testing  
- Mechanical Testing  
- Performance & Approvals Testing

: Accreditation No. 983  
: Accreditation No. 985  
: Accreditation No. 1356



Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)  
MANAGING DIRECTOR

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499


## TEST REPORT

**Client :** Egger Australasia Pty Ltd  
PO Box 697  
Carlton South VIC 3053


**Test Number :** 19-001907  
**Issue Date :** 10/07/2019  
**Print Date :** 11/07/2019

**Specimen :** 3


**Heat release rate (kW/m<sup>2</sup>)**




**Effective heat of combustion (MJ/kg)**



**Smoke production rate ([m<sup>2</sup>/s])**



**Specific extinction area (m<sup>2</sup>/kg)**



103279

35321

Page 7 of 8

© Australian Wool testing Authority Ltd  
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

- Chemical Testing  
- Mechanical Testing  
- Performance & Approvals Testing

: Accreditation No. 983  
: Accreditation No. 985  
: Accreditation No. 1356



Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)  
MANAGING DIRECTOR



# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051


Phone (03) 9371 2400 Fax (03) 9371 2499

## TEST REPORT


**Client :** Egger Australasia Pty Ltd  
PO Box 697  
Carlton South VIC 3053

**Test Number :** 19-001907  
**Issue Date :** 10/07/2019  
**Print Date :** 11/07/2019


Mass loss rate (g/s)




Total heat released (MJ/m<sup>2</sup>)



Mass (g)



Rate of smoke release ([m<sup>2</sup>/s]/m<sup>2</sup>)



103279

35321

Page 8 of 8

© Australian Wool testing Authority Ltd  
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

- Chemical Testing  
- Mechanical Testing  
- Performance & Approvals Testing

: Accreditation No. 983  
: Accreditation No. 985  
: Accreditation No. 1356



Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)  
MANAGING DIRECTOR